

# COVERINGS ETC

**ECCO-CEM<sup>®</sup>**

Technical Specifications

# ECO-CEM - TECHNICAL SPECIFICATIONS

TEST PERFORMED	ASTM	RESULTS
Static coefficient of friction	C-1028	Dry: 0.95 Wet: 0.92
Modulus of rupture	C-120	Dry: 1,800 psi Wet: 800 psi
Modulus of elasticity	C-469	1,75 x 10 <sup>6</sup> psi
Shear strength	D-732	Dry: 1,200 psi Wet: 1,170 psi
Tensile strength	D-209	Dry: 600 psi Wet: 450 psi
Compressive strength	C-170	Dry: 3,900 psi Wet: 3,000 psi
Water vapor permeance	E-96	6.5 perms
Thermal conductivity (k)	C-58	1.43 BTU-In/Hr F
Flame spread and smoke development index	E-84	Flame: 0 index Smoke: 0 index